

Americule Impact Material Formulations

Formulation	Tested at 78-degrees Fahrenheit			10-degrees F	2-Meter Bowling Ball Drop		
	Durometer 000-S	Durometer 000	Durometer 00	Durometer 00	Drop 1	Drop 2	Drop 3
B2	20			50	No Data Available		
B3	30	25		52	No Data Available		
B4		28		55	No Data Available		
B5		33		57	2.75"	5.5"	4.75"
B6		42		60	3.5"	3"	4"
B7		44		60	4"	4.5"	3.75"
B8		50	28	64	4.25"	5.25"	5"
B9		59	36	66	2.5"	3.25"	4"
C0			39	65	3.75"	3.25"	4.25"
C5			61	72	6.25"	5.5"	7"
D0			70	76	10.75"	10.5"	10.75"
D5			75	80	No Data Available		
E0			81	83	No Data Available		